



# ELEMENTS

## HIGH PERFORMANCE

- ✓ 100% Breathable
- ✓ Anti-Stain Properties
- ✓ Long-Lasting
- ✓ Invisible
- ✓ Water Based
- ✓ Safe for Children, Pets and Wildlife when dry

## INDOOR & OUTDOOR

- ✓ Porcelain
- ✓ Sandstone
- ✓ Marble
- ✓ Granite
- ✓ Limestone
- ✓ Slate
- ✓ Terracotta
- ✓ Concrete
- ✓ Bricks & Masonry

# PAVING SHIELD

## ELEMENTS PAVING SHIELD

Is an aqueous high performance impregnation sealant that offers excellent long-lasting protection to porcelain paving. Paving Shield provides exceptional water and oil repellence on treated surfaces without changing the original appearance.

### PREPARATION

Prior to treatment, ensure surfaces are clean, dry and free from cement, grout, debris and algae. If pressure washed allow a minimum of 4 days to fully dry. Test product in an inconspicuous area or on a sample prior to use.

### APPLICATION

Shake prior to use. Apply Paving Shield by roller, mop, saturated brush or low-pressure deck sprayer. Do not allow liquid to pool, remove excess with microfibre cloth. For optimum performance apply a second coat around 30 minutes after first (wet on wet). Surfaces will be touch dry within 1 hour but requires 24 hours to fully cure. **DO NOT APPLY** if rain is forecast within 24 hours. **DO NOT APPLY** if stone temperatures exceed 30°C. [SCAN QR CODE FOR TECHNICAL DATA SHEET, MSDS AND APPLICATION VIDEO.](#)

### COVERAGE

Coverage is dependent on surface porosity. On highly porous surfaces approx. 5-10m<sup>2</sup> per ltr. Second coat and lower porosity surfaces approx. 10-20m<sup>2</sup> per ltr. For porcelain paving  $\geq 20\text{m}^2$  per ltr can be achieved. **THIS PRODUCT IS NOT RECOMMENDED FOR POLISHED SANDSTONE OR GLOSS PORCELAIN.**



Elemental Inks & Chemicals Ltd.  
[www.elemental-ic.com/elements](http://www.elemental-ic.com/elements)

The data shown has been produced by EIC using accepted procedures and testing equipment. The information was accurate on the date of issue. We cannot assume responsibility for results obtained by others. In no event will EIC be liable for damages of any nature arising from the use of the above data. Data is supplied on the condition users will test the material for suitability before commencing application.



SCAN ME